

CLASSIC

Savoy Contract Furniture
PO Box 248
Montoursville, PA 17754
800-233-8953
www.savoyfurniture.com

GRADE

B



RESILIENCE™

THE FAUX LEATHER THAT BUILDS LUXURY INTO PERFORMANCE™

Superior stain resistance

Phthalate-Free

Soft and supple hand

Exceptional durability

CLASSIC



Porcini
SCL-222



Fog
SCL-106



Mortar
SCL-220



Gunite
SCL-214



Sage
SCL-036



Comet
SCL-208



Granite
SCL-019



Pewter
SCL-031



Bedrock
SCL-204



Navy
SCL-027



Granny Smith
SCL-213



Reef
SCL-111



Picholine
SCL-221



Fern
SCL-210



Lake
SCL-107




Appalachian
SCL-202




Maui
SCL-218



Galleon
SCL-212



Blue Ridge
SCL-006



Wave
SCL-224



Admiral
SCL-001



Black
SCL-005



Marshallmallow
SCL-108



Buttercream
SCL-205



Gypsum
SCL-215



Wisp
SCL-225



Horizon
SCL-216



Doe
SCL-016



Citrine
SCL-207



Cashew
SCL-011



Carnation
SCL-206



Buff
SCL-009



Aniseed
SCL-201



Stone
SCL-040



Barley
SCL-203



Flan
SCL-211



Rodeo
SCL-112



British Tan
SCL-008



Papyrus
SCL-029



Taupe
SCL-041



Daffodil
SCL-209



Saffron
SCL-035



Safflower
SCL-223




Persimmon
SCL-030



Mustang
SCL-109



Saddle
SCL-034



American Beauty
SCL-003



Tandoor
SCL-114



Cayenne
SCL-012



Rouge
SCL-032



Claret
SCL-015



Malbec
SCL-217



Mocha
SCL-026



Morel
SCL-219



Burgundy
SCL-010



Grape
SCL-020



Fudge
SCL-018



Chocolate
SCL-014

GENERAL SPECIFICATIONS

CONTENT	Surface: 100% PVC (Phthalate Free) Backing: 100% Polyester
WIDTH	54"
WEIGHT	29 oz.
ROLL SIZE	30 yards
STAIN RESISTANCE	Resilience™



*ACT® Registered Certification Marks

PERFORMANCE SPECIFICATIONS

Abrasion Resistance	500,000+ Double Rubs	ASTM D4157-13 Wyzenbeek
Colorfastness to Light	1000 Hours	AATCC 16.3-2014, Option 3
UV Resistance	1000 Hours	ASTM G154-12a
Colorfastness to Crocking	5.0 Wet 5.0 Dry	AATCC 8-2016
Anti-Microbial	Pass	ASTM G21-13
Anti-Bacterial	Pass	AATCC 147-2011
Mildew Resistance	Pass	ASTM G21-13
Cold Crack	-20°	CFFA 6a-2010
Bleach Resistance	10% Dilution	AATCC 107-2013
Sulfide Stain Resistance	Yes	

FLAMMABILITY REQUIREMENTS**

California Fire Code Technical Bulletin No. 117-2013
 NFPA 260
 UFAC Class I
 ASTM E-84 (Adhered and Unadhered): Class 1 or A
 IMO 2010 FTP Code, Part 8
 FMVSS 302

Suitable For:

Hospitality, Healthcare, Contract, Education, Marine, Automotive, RV, Residential

Reduced Environmental Impact

Phthalate Free
 Lead Free
 BPA Free/TRIS Free/Formaldehyde Free
 Does not contain Conflict Minerals



412 Boston Ave., PO Box 701
 Egg Harbor City, NJ 08215
 Phone: 800.950.3684
 Email: sales@dougind.com

CARE AND CLEANING

Prompt cleaning is always recommended. Cleaning steps are listed by type of stain.

Regular Cleaning and Maintenance

Clean the soiled area with mild soap and water, then rinse with fresh water and wipe dry with a clean cloth.

Dirty
Grime

Food Stains / Oils

Wipe affected area with a soft cloth or soft bristle brush using a non-abrasive cleaner, for example Formula 409 or Fantastik. Rinse with fresh water and wipe dry.

Mustard
Ketchup
Chocolate
Coffee/Tea
Salad Dressing

Healthcare

Clean the soiled area with a 10% solution of Household Bleach and water. It is important to rinse the cleaned area with fresh water after applying the bleach solution.

Blood
Urine
Iodine
Betadine

Difficult Stains

Clean the soiled area with a 50% solution of Isopropyl Alcohol (Rubbing Alcohol) and water. It is important to rinse the cleaned area with fresh water after applying the alcohol solution.

Mascara
Lipstick
Hairspray
Grease
Motor Oil
Soy Sauce
Coffee

The use of commercial vinyl conditioners and protectants is not recommended.

Note: The information in this cleaning guide refers to performance in specific tests conducted under laboratory conditions. This information is not a guarantee that every stain will be removed completely. Some residual ghosting may be present after all cleaning steps are followed.

Resilience™ is a trademark of Nassimi LLC

PROP 65 WARNING: This product may contain a chemical known to the State of California to cause cancer and birth defects or other reproductive harm

**This term and any corresponding data refer to typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions